

LINCOLN® RED MAX® 309LSi

Stainless ▪ AWS ER309Si, ER309LSi

KEY FEATURES

- Engineered surface treatment for weldability control in semiautomatic applications
- High silicon level for increased puddle fluidity and toe wetting
- Q2 Lot® - Certificate showing actual wire composition and calculated ferrite number (FN) available online

WELDING POSITIONS

All

SHIELDING GAS

Short Circuiting Transfer:

90% He/ 7.5% Ar/ 2.5% CO₂

Axial Spray Transfer:

98% Argon/ Balance O₂ or CO₂

CONFORMANCES

AWS A5.9:	ER309Si, ER309LSi
ASME SFA-A5.9:	ER309Si, ER309LSi
ABS:	ER309Si, ER309LSi
CWB/CSA W48-06:	ER309LSi
EN ISO 14343-B:	SS309LSi
ISO 14343:2009:	(23 12 LSi)

TYPICAL APPLICATIONS

- Semiautomatic welding
- Designed for joining stainless steel to mild steel or low alloy steel

DIAMETERS / PACKAGING

Diameter in (mm)	33 lb (15 kg) Steel Spool	500 lb (227 kg) Accu-Trak® Drum	500 lb (227 kg) Accu-Pak® Box
0.035 (0.9)	ED036763	ED036971	ED036927
0.045 (1.1)	ED036764	ED036972	ED036928
1/16 (1.6)	ED036765	ED036973	ED036929

MECHANICAL PROPERTIES⁽¹⁾ – As Required per AWS A5.9

	Yield Strength ⁽²⁾ MPa (ksi)	Tensile Strength MPa (ksi)	Elongation %	Ferrite Number
Requirements - AWS ER309Si, ER309LSi	Not Specified			
Typical Results⁽³⁾ - As-Welded	450 (65)	595 (86)	42	11

WIRE COMPOSITION⁽¹⁾ – As Required per AWS A5.9

	%C ⁽⁴⁾	%Cr	%Ni	%Mo	%Mn
Requirements - AWS ER309Si, ER309LSi	0.03 max	23.0-25.0	12.0-14.0	0.75 max	1.0-2.5
Typical Results⁽³⁾ - As-Welded	0.03	23.5	13.7	0.28	2.0
	%Si	%P	%S	%N ⁽⁵⁾	%Cu
Requirements - AWS ER309Si, ER309LSi	0.65-1.00	0.03 max	0.03 max	Not Specified	0.75 max
Typical Results⁽³⁾ - As-Welded	0.89	0.02	0.01	0.06	0.22

⁽¹⁾Typical all weld metal. ⁽²⁾Measured with 0.2% offset. ⁽³⁾See test results disclaimer. ⁽⁴⁾AWS Requirement for ER309Si is 0.12% max carbon. ⁽⁵⁾Included in 0.50% max. for other elements not specified.

TYPICAL OPERATING PROCEDURES

Diameter, Polarity Shielding Gas	CTWD ⁽⁶⁾ mm (in)	Wire Feed Speed m/min (in/min)	Voltage (Volts)	Approx. Current (Amps)	Deposition Rate kg/hr (lb/hr)	
Short Circuit Transfer						
0.035 in (0.9 mm), DC+ 90% He / 7.5% Ar / 2.5% CO ₂	13 (1/2)	3.0 (120)	20-21	60	0.9 (2.0)	
	13 (1/2)	4.6 (180)	21-23	90	1.4 (3.0)	
	13 (1/2)	5.8 (230)	22-24	105	1.8 (3.9)	
	13 (1/2)	7.6 (300)	23-25	130	2.3 (5.0)	
	13 (1/2)	8.9 (350)	24-26	145	2.7 (5.9)	
	13 (1/2)	10.2 (400)	25-27	155	3.1 (6.7)	
0.045 in (1.1 mm), DC+ 90% He / 7.5% Ar / 2.5% CO ₂	13 (1/2)	2.5 (100)	20-21	80	1.1 (2.8)	
	13 (1/2)	3.2 (125)	21-22	110	1.5 (3.5)	
	13 (1/2)	3.8 (150)	21-23	130	1.7 (4.2)	
	13 (1/2)	4.4 (175)	22-24	145	2.0 (4.8)	
	13 (1/2)	5.6 (220)	23-25	170	2.6 (6.1)	
	13 (1/2)	6.4 (250)	24-26	180	2.9 (6.9)	
0.045 in (1.1 mm), DC+ 98% Ar / 2% O ₂	13 (1/2)	10.2 (400)	23-24	190	3.1 (6.7)	
	13 (1/2)	10.8 (425)	24-25	200	3.3 (7.1)	
	13 (1/2)	11.4 (450)	24-25	210	3.5 (7.5)	
	13 (1/2)	12.1 (475)	25-26	220	3.7 (8.0)	
	0.045 in (1.1 mm), DC+ 98% Ar / 2% O ₂	13 (1/2)	6.1 (240)	22-24	195	2.8 (6.6)
		13 (1/2)	6.6 (260)	23-25	215	3.0 (7.2)
13 (1/2)		7.6 (300)	24-26	245	3.5 (8.3)	
13 (1/2)		8.3 (325)	25-27	250	3.8 (9.0)	
13 (1/2)		9.1 (360)	25-27	275	4.2 (10.0)	
Axial Spray Transfer						

⁽¹⁾Typical all weld metal. ⁽²⁾Measured with 0.2% offset. ⁽³⁾See test results disclaimer. ⁽⁴⁾AWS Requirement for ER309Si is 0.12% max carbon. ⁽⁵⁾Included in 0.50% max. for other elements not specified. ⁽⁶⁾To estimate ESO, subtract 1/8 in (3.2 mm) from CTWD.

IMPORTANT: SPECIAL VENTILATION AND/OR EXHAUST REQUIRED

Fumes from the normal use of some welding products can contain significant quantities of components - such as chromium and manganese - which can lower the 5.0 mg/m³ maximum exposure guideline for general welding fume.

BEFORE USE, READ AND UNDERSTAND THE SAFETY DATA SHEET (SDS) FOR THIS PRODUCT AND SPECIFIC INFORMATION PRINTED ON THE PRODUCT CONTAINER.

Safety Data Sheets (SDS) and Certificates of Conformance are available on our website at www.lincolnelectric.com

TEST RESULTS

Test results for mechanical properties, deposit or electrode composition and diffusible hydrogen levels were obtained from a weld produced and tested according to prescribed standards, and should not be assumed to be the expected results in a particular application or weldment. Actual results will vary depending on many factors, including, but not limited to, weld procedure, plate chemistry and temperature, weldment design and fabrication methods. Users are cautioned to confirm by qualification testing, or other appropriate means, the suitability of any welding consumable and procedure before use in the intended application.

CUSTOMER ASSISTANCE POLICY

The Lincoln Electric Company is manufacturing and selling high quality welding equipment, consumables, and cutting equipment. Our challenge is to meet the needs of our customers and to exceed their expectations. On occasion, purchasers may ask Lincoln Electric for information or advice about their use of our products. Our employees respond to inquiries to the best of their ability based on information provided to them by the customers and the knowledge they may have concerning the application. Our employees, however, are not in a position to verify the information provided or to evaluate the engineering requirements for the particular weldment. Accordingly, Lincoln Electric does not warrant or guarantee or assume any liability with respect to such information or advice. Moreover, the provision of such information or advice does not create, expand, or alter any warranty on our products. Any express or implied warranty that might arise from the information or advice, including any implied warranty of merchantability or any warranty of fitness for any customers' particular purpose is specifically disclaimed.

Lincoln Electric is a responsive manufacturer, but the selection and use of specific products sold by Lincoln Electric is solely within the control of, and remains the sole responsibility of the customer. Many variables beyond the control of Lincoln Electric affect the results obtained in applying these types of fabrication methods and service requirements.

Subject to Change - This information is accurate to the best of our knowledge at the time of printing. Please refer to www.lincolnelectric.com for any updated information.